

Clairalfa Envelopes & Pockets

Clairefontaine paper: a level of performance that makes all the difference

- bulky paper for easy processing
- optimised surface finish, essential factor for good colour reproduction
- very high whiteness 171CIE, possible harmonisation with letters made on Clairalfa paper

A optimised manufacturing process, creating added value

- a reinforced closure, for both adhesive and gummed envelopes
- good flatness of the envelope pile, essential for reliable machine processing
- envelopes delivered in hinged boxes, practical to use, and reusable for the printer

More sustainable envelopes than ever

- a 35g crystal paper window: 85% transparency, 100% biodegradable
- envelopes printed with water-based inks
- paper and envelopes made in France

Substance	gsm	NF EN ISO 536	(+/-2,5%)	80	90
Thickness	µm	NF EN ISO 534	(+/-5)	109	122
Bulk	cm ³ /g	NF EN ISO 534		1.36	1.36
Whiteness	CIE	NF ISO 11475	(+/-3,5%)	171	171
	ISO	ISO 2470-2		112	112
Opacity	%	NF ISO 2471	(+/-3)	94	95
Bendtsen roughness	ml/min	ISO 8791-2	(+/-40)	120	120



Peel and seal :
the most efficient manual closure system:
Peel off the strip and fold down the flap to seal.



Automatic insertion :
gummed closure system suitable for
automatic insertion.



Product certificates and environmental information

- PEFC



Mill certifications

- ISO 14001: Environmental management system
- ISO 9001: Quality management system
- ISO 50001: Energy management system

Made in France

Indicative values. Errors and omissions excepted. Subject to change without notice.
Revision date: 2022/03/18