

# Silk Original

Rebecca **Rock**

## Description

Silk Original has all the advantages of Rough Original in a more satin finish. It further enhances print rendering and offers a softer touch, while retaining a very good grip and hold. Its well-balanced whiteness ensures a natural rendering of your color prints.

Available from 100 to 350 g/m<sup>2</sup>.

## Technical specifications

Substance	g/m <sup>2</sup>	<b>100</b>	<b>120</b>	<b>150</b>	<b>170</b>	<b>200</b>	<b>300</b>	<b>350</b>	NF EN ISO 536
Thickness	µm	110	125	152	168	198	297	346	NF EN ISO 534
Bulk	cm <sup>3</sup> /g	1.09	1.07	1.04	1.03	1	0.99	0.99	NF EN ISO 534
Bendtsen Roughness	ml/min	120	120	120	120	120	60	60	ISO 8791-2
Absolute Humidity	%H <sub>2</sub> O	5.3	5.3	6.0	6.0	6.5	7.0	7.0	NF EN ISO 20287
Relative Humidity	% in the air	42	42	48	48	50	60	60	Sword Measurement
Opacity	%	93	95	97	98	98	>99	>99	NF ISO 2471

These values are not contractual.

Revision date: 2026/05/08

## Certifications



ISO 9001

ISO 14001

ISO 50001